

Mint of the United States at Philadelphia, Pa.,

COINER'S DEPARTMENT,

July 19th 1888

Hon Daniel M. Fox

Superintendent

Sir,

I have the honor to report that the following loss occurred in a sample lot of 1¢ Bronze and 5¢ Nickel Banks, cleaned July 18th with a view of ascertaining their wastage.

	Bronze 1¢	Nickel 5¢
Wt before cleaning	$\begin{array}{r} \text{ozs.} \\ 1458.00 \end{array}$	$\begin{array}{r} \text{ozs.} \\ 1458.00 \end{array}$
" after "	$\begin{array}{r} \text{ozs.} \\ 1417.30 \end{array}$	$\begin{array}{r} \text{ozs.} \\ 1427.20 \end{array}$
Loss in "	$\begin{array}{r} \text{ozs.} \\ 40.70 \end{array}$	$\begin{array}{r} \text{ozs.} \\ 30.80 \end{array}$
	$\begin{array}{r} .0279 \% \end{array}$	$\begin{array}{r} .0211 \% \end{array}$

Very Respectfully
H. Steel
Coiner

Mint of the United States at Philadelphia, Pa.,


COINER'S DEPARTMENT,

July 19, 1889.

W. S. Steel

Coiner.

Report's loss in sample
lot of 1¢ Bronze & 5¢ Nickel
blanks. Cleaned July 18th.
to ascertain wastage.



No. of Enclosures,

[Abstract:] Reports loss in sample lot of 1¢ Bronze & 5¢ Nickel blanks...

Mint of the United States at Philadelphia, Pa.,
Coiner's Department,
July 19, 1888

Hon. Daniel M. Fox
Superintendent

Sir:

I have the honor to report that the following loss occurred in a sample lot of 1¢ Bronze, and 5¢ nickel blanks, cleaned July 18th with a view of ascertaining their wastage.

	Bronze 1¢	Nickel 5¢
Weight before cleaning	<u>Ozs.</u> 1458.00	<u>Ozs.</u> 1458.00
“ after “	<u>Ozs.</u> 1417.30	<u>Ozs.</u> 1427.20
Loss in “	<u>Ozs.</u> 40.70	<u>Ozs.</u> 30.80
	.0279 %	.0211 %

Very Respectfully,
W.S. Steel
Coiner